



**EVEREST PRINT**

Total weight: 270 g/sq.m (+/-7%)  
 Composition: 100% POLYESTER (Polyester membrane)  
 Width: 145/150 cm

Care Instructions:

UNI EN 23758     

Technical properties	Properties mean	Standard reference
Spray Test	Level 5	ISO 4920:2012
Hydrostatic head water column	>7.900 MM	UNI EN 20811:1993
Water vapour permeability	25≤Ret≤30 m2Pa/W (Class 2 – En343)	Internal method
Snagging Test (rotating box - 3000 rotations)	Level 3	ICI test method 444
Abrasion Martindale	50.000 (Level 3)	UNI EN ISO 12947-2

Sublimation print parameters:  
 (sublimation press print machine by MONTI mod. 853)  
 Temp. 200°C – time 70 sec – press. 4 bar – velocity 1,2 m/sec