




## HEINI PRINT

Total weight: 190 g/sq.m (+/-7%)  
Composition: 100% POLYESTER (Hotmelt)  
Width: 145/150 cm

Care Instructions:

UNI EN 23758



Technical properties	Properties mean	Standard reference
Spray Test	Level 2	ISO 4920:2012
Hydrostatic head water column	NOT WATERPROOF (0 MM)	UNI EN 20811:1993
Water vapour permeability	20≤Ret≤30 m2Pa/W (Class 2 – En343)	Internal method
Snagging Test (rotating box - 3000 rotations)	Level 4	ICI test method 444
Abrasion Martindale	50.000 (Level 4)	UNI EN ISO 12947-2

Sublimation print parameters:  
(sublimation press print machine by MONTI mod. 853)  
Temp. 200°C – time 70 sec – press. 4 bar – velocity 1,2 m/sec