



## MARMOLADA


Total weight: 310 g/sq.m (+/-7%)

Composition: 87,6% POLYESTER; 12,4% ELASTAN (Polyester membrane)

Width: 145/150 cm

Care Instructions:

UNI EN 23758



Technical properties	Properties mean	Standard reference
Spray Test	Level 4	ISO 4920:2012
Hydrostatic head water column	>8.000 MM	UNI EN 20811:1993
Water vapour permeability	20≤Ret≤25 m2Pa/W (Class 2 – En343)	Internal method
Snagging Test (rotating box - 3000 rotations)	Level 3,5	ICI test method 444
Abrasion Martindale	50.000 (Level 3,7)	UNI EN ISO 12947-2

Sublimation print parameters:

(sublimation press print machine by MONTI mod. 853)

Temp. 200°C – time 70 sec – press. 4 bar – velocity 1,2 m/sec